

Tab. 1. Właściwości fizyczne materiałów

GATUNEK	Rezystywność [μWm]	Wytrzymałość na zginanie [kg/cm^2]	Gęstość znamionowa [g/cm^3]	Twardość wg Shore'a [$^{\circ}\text{Sh}$]
ELEKTROGRAFITY				
DE7	61	303	1,67	83
DE7000	51	380	1,71	83
EG0/EG0R	12	130	1,55	37
EG116	53,5	165	1,63	70
EG116S	47	225	1,6	72
EG12	21	188	1,58	67
EG14D	47	225	1,6	72
EG18	18	205	1,68	56
EG224	49	120	1,6	60
EG236	53,5	125	1,48	61
EG236S	47	165	1,51	63
EG251	52	140	1,63	60
EG259	52	190	1,75	70
EG260	12	125	1,55	37
EG275 / ME778	53,5	175	1,63	73
EG283	61	100	1,46	59
EG295AC	61	100	1,47	60
EG6749N	25	200	1,64	67
EG8101	52	145	1,63	65
ME353	47	450	1,8	93
ME373	60	400	1,8	93
ME377	60	130	1,55	65
ME393	67	350	1,75	93
N19	61	193	1,61	76
N19X	66	240	1,66	68
N48	71	138	1,58	59
N6000	61	140	1,55	66
SA35	53	165	1,54	61
SA40	61	130	1,52	55
SA45	66	102	1,49	50
SA4548	66	96	1,49	50
TA35	53	185	1,58	58
TA35R	53	190	1,6	60
TA45R	66	124	1,55	56
WĘGLE TWARDE I WĘGLOGRAFITY				
C12	570	45	1,52	32
H100	40	135	1,7	30
PM50P	190	85	1,65	27
GRAFIT NATURALNY				
634	25	52	1,28	16
HM24	24	45	1,49	22
METALOGRAFIT				
CM1S	0,32	610	5,3	12
CM3H	0,19	270	4,3	12
CM5H	0,3	180	4	15
CM9	2,5	315	2,9	31
GM61	13	145	2,58	30
SM3	2,05	165	2,5	29
SM9173	0,075	475	5,2	18
GRAFIT IMPREGNOWANY METALEM				
DM4D	3	520	3	45
GRAFIT Z DOMIESZKAMI ŻYWIC				
IM26 / IM9101	102	390	1,85	47
IM31 / IMX31	270	205	1,7	38
IM6	660	170	1,55	35
IM8876	180	415	1,83	48